



ETCH PRIMER 1K

H19

VERSION: 170623
Page:1/3

ANTICORROSIVE PRIMER

DEFINITION

AIRCOLOR ETCH PRIMER 1K is a single component adhesive promoter with anti-corrosive power. It stands out because of its excellent adhesion on various surfaces such as galvanized metals, aluminium, steel, among others.

TECHNICAL CHARACTERISTICS

- Adhesion promoter on various surfaces.
- Anti-corrosive protection.
- Very fast drying.
- We recommend it be used as an adhesive promoter. Refinish with a 1k or 2k primer for a better result.
- It can be used for both partial repairs and patches.
- We recommend applying thin and even coats for better results.
- It has a transversal nozzle that allows you to adjust how its applied, horizontally or vertically.



PHYSICAL CHARACTERISTICS

Nature:	Resin mixture
Propellant:	DME
Colour:	Grey
Specific Weight:	0,8 Kg/l
Extrusion Speed:	0,95 ± 0,3 g/s
Aerosol Pressure:	4,60 ± 0,5 bar a 25°C
Yield:	2 m ² /spray
Dry film thickness:	7-15 µ/coat
Temperature resistance:	< 50 °C
VOC:	701 g/l Application 2004/42/EC - IIB (e)(840)

SURFACE OR BACKING PREPARATION

PROCESS		Steel	Aluminium	Galvanized
	P360	<i>Optional</i>	<i>Advisable</i>	<i>Optional</i>
	DA93	✓	✓	✓

APPLICATION METHOD

				
Nozzle kind: Transversal White /Yellow	1'	20-25 cm	1-2 coats	20'


DRYING TIMES

		
20°C	12'	15' -2h

REMARKS

Area must be clean, dry and free of grease and dust.
Shake the aerosol before use for 1 minute after hearing the steel mixing balls move.
Protect the areas that will not be painted.
Carry out test spray. Check the colour.

EQUIPMENT CLEANING



SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +10°C and +25°C with relative air humidity of maximum 60%.

SHELF LIFE

One year in unopened original packaging.

For any technical information contact with our Customer Attention Service or our Technical Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.